



IRMRA

INDIAN RUBBER MANUFACTURERS RESEARCH ASSOCIATION

Affiliated to Ministry of Commerce & Industry (Government) of India)

(A NABL (ISO - 17025-2005) Accredited Laboratory)

E-mail : info@irmra.org • Website : www.irmra.org

EVALUATION REPORT

Report No : RPT / 1160(A) / 15-16	10 Sep 2015	Page 1 of 3
-----------------------------------	-------------	-------------

--- CUSTOMER DETAILS ---

Customer Name & Address :	
M/s.Sunflex Recycling Pvt Ltd 274/4, Shital Estate,Opp. Gujarat High Court, S.G.Highway,Sola, Ahmedabad, Gujarat, INDIA 380060	
Contact Person :	Sunit Patel
Telephone No :	27662051
Customer Letter Ref No with Date :	Dated 18 Aug 2015
Date of Receipt :	18 Aug 2015
Any Other Information like witness / third party	Reclaim Rubber

--- SAMPLE DETAILS ---

Sample Code / Description :	Nylon Tyre Reclaim Rubber
Product Specification :	IS-7490-1997

--- REPORT DETAILS ---

Description of Report	Page Nos
RPT / 1160(A) / 15-16 - M & R -	2 of 3
RPT / 1160(A) / 15-16 - C & I -	3 of 3

Terms and Conditions

1. Sample was not drawn by IRMRA, unless otherwise stated.
2. The result enclosed are only related to the sample submitted to us.
3. The report shall not be reproduced except in full without prior written permission of laboratory.
4. Information contained in this letter / or enclosed reports is/are purely meant for your guidance and should not be used for litigation/evidence/advertisement, without prior permission from laboratory.

Prepared and Checked By



Authorized Signatory



IRMRA

INDIAN RUBBER MANUFACTURERS RESEARCH ASSOCIATION

Affiliated to Ministry of Commerce & Industry (Government of India)

(A NABL (ISO - 17025-2005) Accredited Laboratory)

E-mail : info@irmra.org • Website : www.irmra.org

TECHNICAL REPORT / M & R

RPT / 1160(A) / 15-16 - M & R

10 SEP 2015

Page 2 of 3

Sample : Nylon Tyre Reclaim Rubber Specn. IS-7490-1997

Test (Condition)	Method	Unit	Specified Value	Observed Value
Tensile Strength (Before Ageing.)	IS 6306 : RR8	N/mm ²	-	5.1
Elongation at break (Before Ageing.)	IS 6306 : RR8	%	-	260
Mooney Viscosity (ML1+4 @100 °C.) (On Raw)	IS 6306 : RR7	MU	-	35
Mooney Viscosity (ML1+8@125°C) (On Raw)	IS 6306 : RR7	MU	--	28

Prepared and Checked By

Authorized Signatory





IRMRA

INDIAN RUBBER MANUFACTURERS RESEARCH ASSOCIATION

Affiliated to Ministry of Commerce & Industry (Government of India)
(A NABL (ISO - 17025-2005) Accredited Laboratory)
E-mail : info@irmra.org • Website : www.irmra.org

TECHNICAL REPORT / C & I

RPT / 1160(A) / 15-16 - C & I


10 SEP 2015

Page 3 of 3

Sample : Nylon Tyre Reclaim Rubber Specn. IS-7490-1997

Test (Condition)	Method	Unit	Specified Value	Observed Value
Ash Content (On Raw-By TGA)	ASTM E-1131	% by Wt	-	5.0
Carbon Black Content (On Raw-By TGA)	ASTM E-1131	% by Wt	-	28.4
Density	IS-6306:RR2	gm/cc	-	1.13
Acetone Extractable Matter (On Raw)	IS-6306:RR4	%	-	15.5
Total Rubber Hydrocarbon (On Raw-By TGA)	ASTM E-1131	% by Wt	-	51.1
Volatile Matter (On Raw)	IS-6306:RR1	%	-	0.99

Encl.: TGA graph.


Prepared and Checked By


Authorized Signatory

